

STRUCTUROC H-ULTRA-MODIFIED

High Strength Mortar with Prolonged Working Time

STRUCTUROC H ULTRA-MODIFIED is a high early strength repair material, modified to provide for longer setting times and requires only the addition of water to produce a permanent repair for concrete. **STRUCTUROC H ULTRA-MODIFIED** is dimensionally stable and forms an integral bond with the existing concrete to restore its structural integrity. **STRUCTUROC H ULTRA-MODIFIED** is designed for horizontal repairs and can be placed at thicknesses ranging from 1/4" (6 mm) up to 12" (300 mm) in a single lift. This product can be extended with up to 50% of clean pea gravel to produce a high strength repair concrete.

USES

Repair of spalled and damaged concrete structures due to wear, abrasion, temperature and other damage factors.

TYPICAL USES:

- Fast repair and return to service of damaged industrial concrete floor
- Repairs to concrete floors prior to the installation of **SOLHYDFLOW** self-leveling products
- Repair and creation of concrete slopes, drains and trenches
- Repair of concrete walls, bases and columns
- Repair of bridge decks, parking decks and ramps
- Repair of balconies

PRODUCT FEATURES

- Prolonged working time
- Easy to pump & pour and easy to finish
- Meets or exceeds requirements of ASTM C928/C928M-09
- Permanent repair of concrete
- Excellent bond strength
- Dimensionally stable, resistant to shrinkage and cracking
- Can be applied at variable thicknesses
- Freeze/thaw resistant
- Extremely resistant to wear and abrasion
- Rapid and early strength
- No bonding agent required
- Easy to use
- Meets MTQ requirements
- Can be overcoated within 12 hours after placement

SURFACE PREPARATION

Proper repairs depend upon a solid bond between mortar and base surface. Thoroughly clean and roughen subject area. Remove any curing compound, grease, oil, loose carbonated concrete, dirt, dust etc... from exposed slab. Sawcut area perimeter to a depth of at least 1/4" (6 mm). Use water under moderate pressure to flush and further clean area. If possible, saturate area at least 12 hours prior to applying mortar. During application, area should be saturated but free of standing water.

PRIMING

No primer required.

ESTIMATING / YIELD

STRUCTUROC H ULTRA-MODIFIED is packaged in 50 lbs (22.7 kg) polyethylene bags or plastic pails. Yields 0.42 ft³ (12 L) when mixed with 2 1/2 quarts (2.4 L) of potable water that will cover approx. 11 ft² (1m²) at a thickness of 1/2" (12 mm). This product when extended with 50%, by volume, of 3/8" (10 mm) pea gravel and will yield 0.57 ft³ (16 L) of volume. Also available in 4.5 kg pails.

PHYSICAL MATERIAL PROPERTIES

COMPRESSIVE STRENGTH

[(ASTM 109*, 2" (50 MM) CUBES] @ 72°F (22.2°C)

Time	Mpa	PSI
3 hours	20.0	3000
1 day	40.0	5000
3 days	48.0	7000
7 days	59.0	8500
28 days	70.0	10 000

FREEZE/THAW RESISTANCE ASTM C-666 B

Cycles	Durability factor (RDF)
300	96%

FLEXURAL STRENGTH ASTM C78

7 days	8.2 Mpa	1200 PSI
--------	---------	----------

SET TIME ASTM C191* @ 70°F (21°C)

Initial	65 minutes
Final	85 minutes

BOND STRENGTH ASTM C-882

1 day	8.8 MPa	1300 PSI
7 days	12.2 MPa	1800 PSI

SCALING RESISTANCE ASTM C-672

50 cycles	0	Loss 150 gr/m ²
-----------	---	----------------------------

LENGTH CHANGE ASTM C-157 WITH C-928 MODIFICATION

	Air cure	Water cure (immersion)
7 days	- 0.049	+ 0.027
28 days	- 0.060	+ 0.032

SOLHYDROC

STRUCTUROC H-ULTRA-MODIFIED

High Strength Mortar with Prolonged Working Time

PRECAUTIONS / RESTRICTIONS

Apply to pre saturated surface only
Do not apply on fresh concrete
Do not use bonding agent
Do not apply at temperature under 41°F (5°C)
Do not add admixture to this product

PRODUCT MIXING

Place mixers on proximity to repair area. Approximate initial set of **STRUCTUROC H ULTRA-MODIFIED** is 90 minutes @ 72°F (22°C). Mix only an amount that can be placed and finished before initial set. Place recommended amount of clean water into mixer, add **STRUCTUROC H ULTRA-MODIFIED**, mix for 2 minutes (if extended, add aggregate at this point) and continue to mix until a smooth mixture is obtained. Dispense directly into pump or wheelbarrows. Discard any material that stiffens. Do not retemper. For large pours or temperatures that are below 41°F (5°C) or above 85°F (35°C) contact your local SOLHYDROC representative.

PRODUCT APPLICATION

No bonding agent is necessary with STRUCTUROC H ULTRA-MODIFIED. Upon completion of mixing, place material in repair area. Place from one side of site only; not toward middle from opposite directions.

FINITION AND CURING

Level and screed material to proper height. Float edges with wooden or magnesium trowel only. As soon as the repaired surface has sufficiently hardened apply wet burlap or rags to finished area and cover with polyethylene or keep water ponded on patch, for a minimum of 2 hours.

RECOMMENDED TOOLS

The following tools will assure a cost effective, satisfactory installation:
Steel, Wooden or Magnesium Trowels
3/4" Heavy Duty drill with mixing paddles
Mortar mixer (for large volume)

CLEANING

Use water to clean all tools immediately after use.

STORAGE

Store in cool dry area avoiding all moisture. Can be kept in unopened bags for 12 months.

SAFETY

See Material Safety Data Sheet.

Contains Portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water. Avoid breathing dust.

SOLHYDROC WARRANTS that the product conforms to its chemical description and is reasonably fit for the purpose stated on its Technical Bulletin when used in accordance with its directions. SOLHYDROC makes NO OTHER WARRANTY either expressed or implied. Buyer assumes all risk in handling.

For Professional Use Only

www.solhydroc.com